

Listing of Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

1-53. (Cancelled)

54. (Currently Amended) An elastomeric glove that comprises:

a substrate body shaped to the contours of a hand, said substrate body including a layer made of at least one elastomeric block copolymer, said substrate body having an inside surface and an outside surface;

a chemical protection layer overlying said outside surface of said substrate body, said chemical protection layer being formed from a polymeric material that consists essentially of at least one crosslinked, modified silicone elastomer, said crosslinked modified silicone elastomer imparting relative chemical resistance to the glove;

a donning layer overlying the inside surface of said substrate body; and

an optional outer layer overlying said chemical protection layer;

wherein the chemical protection layer faces an external, environment-exposed surface of the elastomeric glove and the donning layer faces an internal, body-contacting surface of the elastomeric glove.

55. (Previously Presented) The elastomeric glove of claim 54, wherein said modified silicone elastomer is selected from the group consisting of phenyl-modified silicones, vinyl-modified silicones, methyl-modified silicones, fluoro-modified silicones, alkyl-modified silicones, alkoxy-modified silicones, alkylamino-modified silicones, and combinations thereof.

56. (Previously Presented) The elastomeric glove of claim 54, wherein said modified silicone elastomer is selected from the group consisting of phenyl-modified silicones, vinyl-modified silicones, methyl-modified silicones, and fluoro-modified silicones.

57. (Previously Presented) The elastomeric glove of claim 54, wherein said modified silicone elastomer contains a diphenyl-modified dimethylsilicone.

58. (Previously Presented) The elastomeric glove of claim 54, wherein said chemical protection layer has a thickness of from about 0.01 millimeters to about 0.30 millimeters.

59. (Previously Presented) The elastomeric glove of claim 54, wherein said chemical protection layer has a thickness of from about 0.01 millimeters to about 0.20 millimeters.

60. (Currently Amended) The elastomeric glove of claim 54, wherein said chemical protection layer defines the external, environment-exposed ~~a grip~~ surface of the elastomeric glove.

61. (Currently Amended) The elastomeric glove of claim 54, wherein said outer layer defines the external, environment-exposed ~~a grip~~ surface of the elastomeric glove.

62. (Previously Presented) The elastomeric glove of claim 54, wherein the elastomeric block copolymer of the substrate body is selected from the group consisting of styrene-ethylene-butylene-styrene block copolymers, styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-isoprene block copolymers, styrene-butadiene block copolymers, and combinations thereof.

63. (Previously Presented) The elastomeric glove of claim 54, wherein the elastomeric block copolymer is a styrene-ethylene-butylene-styrene triblock copolymer.

64. (Cancelled)

65. (Currently Amended) The elastomeric glove of claim 54 64, wherein said donning layer contains syndiotactic 1,2 polybutadiene.

66. (Currently Amended) The elastomeric glove of claim 54 64, further comprising a lubricant layer overlying an inside surface of said donning layer.

67. (Currently Amended) An elastomeric glove that comprises:

a substrate body shaped to the contours of a hand, said substrate body including a layer made of at least one elastomeric block copolymer selected from the group consisting of styrene-ethylene-butylene-styrene block copolymers, styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-isoprene block copolymers, styrene-butadiene block copolymers, and combinations thereof, said substrate body having an inside surface and an outside surface;

a chemical protection layer covering said outside surface of said substrate body, said chemical protection layer being formed from a polymeric material that consists essentially of at least one crosslinked, modified silicone elastomer selected from the group consisting of phenyl-modified silicones, vinyl-modified silicones, methyl-modified silicones, fluoro-modified silicones, alkyl-modified silicones, alkoxy-modified silicones, alkylamino-modified silicones, and combinations thereof, said crosslinked modified silicone elastomer imparting relative chemical resistance to the glove, wherein said chemical protection layer has a thickness of from about 0.01 millimeters to about 0.20 millimeters;

a donning layer overlying the inside surface of said substrate body; and
an optional outer layer overlying said chemical protection layer;
wherein the chemical protection layer faces an external, environment-exposed
surface of the elastomeric glove and the donning layer faces an internal, body-
contacting surface of the elastomeric glove.

68. (Previously Presented) The elastomeric glove of claim 67, wherein said modified silicone elastomer is selected from the group consisting of phenyl-modified silicones, vinyl-modified silicones, methyl-modified silicones, and fluoro-modified silicones.

69. (Previously Presented) The elastomeric glove of claim 67, wherein said modified silicone elastomer contains a diphenyl-modified dimethylsilicone.

70. (Previously Presented) The elastomeric glove of claim 67, wherein the elastomeric block copolymer is a styrene-ethylene-butylene-styrene triblock copolymer.